

PPG Coatings Nederland BV
Oceanenweg 2
NL 1047 BB Amsterdam
NETHERLANDS

Eurofins Product Testing Denmark A/S
Smedeskovvej 38
8464 Galten
Denmark

DK-CustomerSupport@cpt.eurofinseu.com
www.eurofins.com

TEST REPORT

20 November 2025

Sample Information

Sample name	Sigma Torno Aqua Semi-Gloss
Sample reception	29/10/2025
Sample no.	392-2025-00529204
Analysis period	05/11/2025 - 17/11/2025

Brief Evaluation of the Result

Type of analysis	Conclusion	Standard
Migration of certain elements	Pass	EN 71-3:2019 + A1:2021, Category III

Full details based on the testing and direct comparison with limit values are available in the following pages



Morten Vestergaard Pedersen
Analytical Service Manager



Pernille Krintel
Business Development Manager, MSc. Medicinal Chemistry

*: Not accredited

<: Less than

>: Greater than

LOD: Limit of detection

Um(%): The expanded uncertainty Um(%) equals 2 x RSD%. For further information please visit www.eurofins.dk/uncertainty

The analysis are carried out on the sample(s) as received and the result(s) are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety.

⌘: Internal test method

n.d: Not detected

n.m: Not measurable

LOQ: Limit of quantification

Results

392-2025-00529204 (Sigma Torno Aqua Semi-Gloss)

Code	Name	Limits – Category III [mg/kg]	Result [mg/kg]	LOD [mg/kg]	Um(%)
PSH8F	Migration of Certain Elements				
	Aluminium (Al)	≤ 28130	584	10	-
	Antimony (Sb)	≤ 560	< 10	10	-
	Arsenic (As)	≤ 47	< 10	10	-
	Barium (Ba)	≤ 18750	< 10	10	-
	Boron (B)	≤ 15000	< 10	10	-
	Cadmium (Cd)	≤ 17	< 8	8	-
	Chromium (Cr) #1	-	< 0.025	0.025	-
	Chromium (III)	≤ 460	< 5	5	-
	Chromium (VI)	≤ 0.053	< 0.025	0.025	-
	Cobalt (Co)	≤ 130	< 10	10	-
	Copper (Cu)	≤ 7700	< 10	10	-
	Lead (Pb)	≤ 23	< 10	10	-
	Manganese (Mn)	≤ 15000	< 10	10	-
	Mercury (Hg)	≤ 94	< 10	10	-
	Nickel (Ni)	≤ 930	< 10	10	-
	Selenium (Se)	≤ 460	< 10	10	-
	Strontium (Sr)	≤ 56000	< 10	10	-
	Tin (Sn)	≤ 180000	< 3.2	3.2	-
	Organic Tin #2	≤ 12	< 0.1	0.1	-
	Zinc (Zn)	≤ 46000	650	10	-

Method Reference

BS EN 71-3:2019 + A1:2021 - Migration of Certain Elements
 General Elements : BS EN 71-3:2019 + A1:2021 [ICP-MS]
 Soluble Chromium (VI) : BS EN 71-3:2019 + A1:2021 [IC-UV-Vis]
 Soluble Organic Tin : BS EN 71-3:2019 + A1:2021 [GC-MS]

Comment

Note: 1 mg/kg = 1ppm = 0.0001%

#1 – If the migration of total Chromium exceeded the screening limit of Chromium (VI), the migration of Chromium (VI) was verified.

#2 – If migration of tin exceeded the screening limit of organic tin, the migration of organic tin was verified. The migration of organic tin is calculated by adding the migration values expressed as tributyltin for all the single organic tin compounds.

- Sample tested: coating, evaluated as Coating according to EN 71-3, category III

- Test performed at Eurofins Testing Technology (Shenzhen) Co., Ltd.

*: Not accredited

<: Less than

>: Greater than

LOD: Limit of detection

Um(%): The expanded uncertainty Um(%) equals 2 x RSD%. For further information please visit www.eurofins.dk/uncertainty

The analysis are carried out on the sample(s) as received and the result(s) are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety.


⌘: Internal test method

n.d: Not detected

n.m: Not measurable

LOQ: Limit of quantification

Picture of Sample



Version History

Report date	Report number	Modification
20/11/2025	392-2025-00529204_XN_EN	Current version

*: Not accredited

<: Less than

>: Greater than

LOD: Limit of detection

Um(%): The expanded uncertainty Um(%) equals 2 x RSD%. For further information please visit www.eurofins.dk/uncertainty

The analysis are carried out on the sample(s) as received and the result(s) are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety.

⌘: Internal test method

n.d: Not detected

n.m: Not measurable

LOQ: Limit of quantification