

CLASSIFICATION OF REACTION TO FIRE PERFORMANCE IN ACCORDANCE WITH EN 13501-1:2007+A1:2009

Classification no.	2017-Efectis-R001328
Sponsor	PPG Coatings Nederland B.V. Amsterdamseweg 14 1422 AD UITHOORN THE NETHERLANDS
Product name	Coating, type Sigmacryl Décor Matt
Prepared by	Efectis Nederland BV
Notified body no.	1234
Author(s)	E.O. van der Laan M.Sc. A.J. Lock
Project number	ENL-16-001139
Date of issue	August 2017
Number of pages	5

1. INTRODUCTION

1.1 PRODUCT NAME

This classification report defines the classification assigned to **Coating, type Sigmacryl Décor Matt**, in accordance with the procedures given in EN 13501-1:2007+A1:2009.

2. DETAILS OF CLASSIFIED PRODUCT

2.1 GENERAL

The product, **coating, type product Sigmacryl Décor Matt**, is as wall- and ceiling covering (paint).

2.2 MANUFACTURER

PPG Coatings Nederland B.V.
Amsterdamseweg 14
1422 AD UITHOORN
THE NETHERLANDS

2.3 PRODUCT DESCRIPTION

According to the sponsor the product is from inside out composed of:
Wall paint based on acrylic resin in full shade yellow (UY)

The product:

- has a density of approx. 1.4 kg/dm³
- is painted in two layers
- with a total consumption of +/- 285 gr/m²
- in a layer thickness of approx. 70 µm

3. STANDARDS, REPORTS, RESULTS AND CRITERIA IN SUPPORT OF THIS CLASSIFICATION

3.1 APPLICABLE (PRODUCT) STANDARDS

EN ISO 11925-2:2010	Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test
EN 13823:2010+A1:2014	Reaction to fire tests for building products - Building products, excluding floorings exposed to the thermal attack by a single burning item
EN 13501-1:2007+A1:2009	Fire classification of construction products and building elements Part 1: Classification using data from reaction to fire tests

3.2 REPORTS

Name of Laboratories	Name of sponsor	Report ref. no.	Test method
Efectis Nederland BV THE NETHERLANDS	PPG Coatings Nederland B.V. THE NETHERLANDS	2017-Efectis-R001182 2017-Efectis-R001183	EN ISO 11925- 2:2010 EN 13823:2014

3.3 TEST RESULTS

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
EN ISO 11925-2				
surface flame impingement	Fs ≤150 mm	6	29	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	33	-
	Ignition of filter paper		-	Compliant
EN 13823				
	FIGRA _{0.2MJ} [W/s]	3	0	-
	FIGRA _{0.4MJ} [W/s]		0	-
	THR _{600s} [MJ]		0.7	-
	LFS < edge		-	Compliant
	SMOGRA [m ² /s ²]		0.0	-
	TSP _{600s} [m ²]		26	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant

3.4 CLASSIFICATION CRITERIA

Fire classification of construction products and building elements Excluding floorings and linear pipe thermal insulation products			
Classification criteria			
Class	B	C	D
Test method(s)			
EN ISO 11925-2 Exposure = 30 s	F _s ≤ 150 mm within 60 s Ignition of the paper in EN ISO 11925-2 results in a d2 classification.		
EN 13823	FIGRA _{0,2 MJ} ≤ 120 W/s LFS < edge of specimen THR _{600s} ≤ 7.5 MJ	FIGRA _{0,4 MJ} ≤ 250 W/s LFS < edge of specimen THR _{600s} ≤ 15 MJ	FIGRA _{0,4 MJ} ≤ 750 W/s
Additional classification			
Smoke production	s1 = SMOGRA ≤ 30 m ² /s ² and TSP _{600s} ≤ 50 m ² ; s2 = SMOGRA ≤ 180 m ² /s ² and TSP _{600s} ≤ 200 m ² ; s3 = not s1 or s2		
Flaming Droplets/particles	d0 = no flaming droplets/ particles in EN 13823 within 600 s; d1 = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s; d2 = not d0 or d1.		

4. CLASSIFICATION AND FIELD OF APPLICATION

4.1 REFERENCE OF CLASSIFICATION

This classification has been carried out in accordance with clause 11 of EN 13501-1:2007+A1:2009.

4.2 CLASSIFICATION

The product, **coating type Sigmacryl Décor Matt**, in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0

Reaction to fire classification: B – s1, d0

4.3 FIELD OF APPLICATION

This classification is valid for the following product parameters:

Thickness	Two layers of in total approx.75 µm
Surface density	Approx. 285 ±5% g/m ²

This classification is valid for the following end use applications:

Substrate	Non-combustible (class A1/A2 according to EN 13238:2010)
Application	Walls and ceilings
Air gap	Not applicable
Methods and means of fixing	Paint roller, paint brush and paint sprayer
Joints	Not applicable
Other aspects of end use conditions	All colours

4.4 DURATION OF THE VALIDITY OF THIS CLASSIFICATION REPORT

There are no limitations in time on the validity of this report.

5. LIMITATIONS

This classification document does not represent type approval or certification of the product.



E.O. van der Laan M.Sc.
 Project leader reaction to fire



A.J. Lock
 Project leader reaction to fire